



# SKIMCOAT

## Thin Coat Plaster

### Product Data and Submittal Sheet

#### Description

- **SKIMCOAT** is a gypsum-based thin plaster which can be applied on wide range of surfaces.
- **SKIMCOAT** is a multipurpose plaster for gypsum and cement based undercoat plasters, masonry and plasterboard surfaces.
- Its long workability time enables an easy application with a low waste rate.
- **SKIMCOAT** can be applied easily. Corrects cracks and defects on the surfaces.
- It is easy to prepare **SKIMCOAT** mortar compare to conventional plasters.
- **SKIMCOAT** creates a smooth surface.
- Easy to use for repairs and maintenance.
- **SKIMCOAT** provides white surfaces.

#### Method of Application

- Dust and substances preventing adherence on the surface must be removed before the application.
- 25 kg of **SKIMCOAT** should be mixed with 11,5-12 ltrs of clean water.
- Add some water in a clean bucket. Add **SKIMCOAT** until it covers the water surface. Wait for a few minutes, then mix the mortar with a mechanical whisk until it gains a right consistency for application.
- Mortar in the bucket should be used within approximately 60 minutes.
- **SKIMCOAT** is applied to the whole surface with a trowel and to finish the application, second coat of **SKIMCOAT** is applied. Total thickness of **SKIMCOAT** may vary according to substrate.
- Several further trowel applications are needed for the desired surface.
- Polish with wetted trowel to achieve a flat, smooth surface.
- For 1mm of application per 1m<sup>2</sup> approximately 1,1 kg of **SKIMCOAT** is consumed.

#### Recommendations

- It is recommended to apply jointing tape first where necessary.
- Use a low-speed mechanical whisk.
- Dry and hot surfaces should be dampened before the application.
- Do not add any water or plaster to the mortar after mixing completed.

**RIGHTFINISH**

# SKIMCOAT

## Thin Coat Plaster

### Storage Conditions

- Maximum 2 pallets of **SKIMCOAT** bags should be stacked one on top of another.
- Bags are recommended to be consumed within 9 months provided that they are stored on pallet in a dry and indoor environment.
- Poor storage conditions or exceeding shelf life may reduce **SKIMCOAT**'s performance.

### Standard

- **SKIMCOAT** complies with EN 13279-1 type C6/20/2. It is conforming with ISO 9001: 2015 and manufactured under a quality system which is independently audited and certified.
- All RIGHTFINISH products are conforming with ISO 14001: 2015 and manufactured under a quality system which is independently audited and certified.
- With GREENGUARD Gold Certification and qualifies as a low VOC emitting material.

### Technical Specification

Water / Plaster ratio	11,5-12 ltrs water to 25 kg <b>SKIMCOAT</b>
Setting time starts	> 60 minutes (according to EN 13279-1)
Final setting time	> 90 minutes
Consumption	~ 1.1 kg / m <sup>2</sup> for each 1 mm thickness
Compressive strength	> 2 N / mm <sup>2</sup>
Bulk density (powder)	~ 800 kg / m <sup>3</sup>
Dry weight	~ 1,25 kg /m <sup>2</sup> .cm
Reaction to Fire	A1

### Packaging

Type	Kraft bags
Net weight	25 kg ±%2

05/2020\_Rev:02

PK-E01\_31